

ABSTRACT OF THE DISCLOSURE

In a toner having toner particles containing at least a colorant, a release agent and a polar resin, and an inorganic fine powder, the polar resin contains
5 a polyester resin obtained by carrying out polymerization in the presence of a titanium chelate compound as a catalyst, and has an acid value in a specific range. The toner particles are granulated in an aqueous medium and have a weight-average particle
10 diameter in a specific range.